



# PALAR-SANAT-CO

## TECHNICAL DATA

### PALMAG(GAN-90)

PRODUCT TYPE	Hot Gunning Mix
Maximum service temperature	1680 Ć
Main component	Magnesit
Type of bond	chemical - ceramic
Packing	big bag
Storage	6 month
Installation method	gunning
Maximum grain size	0-3 mm
Water required for mixing on site	At Nozzel

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

### CHEMICAL ANALYSIS

MgO	Min	87	%
Fe <sub>2</sub> O <sub>3</sub>	Max	3	%
SiO <sub>2</sub>	Max	6	%

### PHYSICAL PROPERTIES

Bulk density	*****	gr/cm <sup>3</sup>
Apparent Porosity	*****	Vol -%

### Cold crushing strength ccs

after 5 hr drying at 110 Ć	.....	Kg/cm <sup>2</sup>
after 5 hr firing at 1200 Ć	.....	Kg/cm <sup>2</sup>