



TECHNICAL DATA

PALGUN-60

PRODUCT TYPE	Alumina Gunning Regular Cement
Main component	fireclay
Type of bond	hydraulic
Maximum service temperature	1450 C°
Installation method	Gunning
Storage	6 month
Packing	25 Kg sacks
grain size	0 - 3 mm
Water required for mixing on site	At Nozzle

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

CHEMICAL ANALYSIS
(Calcined basis)

Al ₂ O ₃	Min	60	%
SiO ₂	Max	30	%
Fe ₂ O ₃	Max	1.8	%
CaO	Max	6.5	%

PHYSICAL PROPERTIES

Bulk density	Min	2.1	gr/cm ³
--------------	-----	-----	--------------------

Cold crushing strength)

after 5 hr drying at 110 Ć	Min	400	Kg/cm ²
after 5 hr drying at 1200 Ć	Min	250	Kg/cm ²

p.o.box : 81395-519 ISFAHAN-IRAN Tel/Fax : (+98311)-6614006 - 6615258 - 6641292
www.palarsanat.com [Email:info@palarsanat.com](mailto:info@palarsanat.com)