



PALAR-SANAT-CO

TECHNICAL DATA

PALmor-60

PRODUCT TYPE	mortar Air seting
Main component	low iron fireclay & Bauxite
Type of bond	chemical - ceramic
Maximum service temperature	1500 C°
Installation method	Traveling
Storage	12 month
Packing	25 Kg sacks
grain size	0 - 0.6 mm
Water required for mixing on site	40 - 45 litres per 100 Kg of dry material

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

CHEMICAL ANALYSIS (Calcined basis)

	Min	Max	Units
Al ₂ O ₃	60		%
SiO ₂	34		%
Fe ₂ O ₃	0.8		%
CaO	0.3		%

PHYSICAL PROPERTIES

Bulk density	Max	0	gr/cm ³
--------------	-----	---	--------------------

Cold crushing strength (c.c.s)

after 5 hr drying at 110 C°	Min	0	Kg/cm ²
after 5 hr firing at 1000 C°	Min	0	Kg/cm ²