



TECHNICAL DATA

PRC-95

PRODUCT TYPE	Dense Refractory Castable Regular Cement
Main component	Tabular Alumina
Type of bond	hydraulic
Maximum service temperature	1750 C°
Installation method	casting - Vibrating
Storage	6 month
Packing	25 Kg sacks
grain size	0 - 5 mm
Water required for mixing on site	7 - 10 litres per 100 Kg of dry material

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

CHEMICAL ANALYSIS
(Calcined basis)

Al ₂ O ₃	Min	95	%
SiO ₂	Max	1	%
Fe ₂ O ₃	Max	0.8	%
CaO	Max	5	%

PHYSICAL PROPERTIES

Bulk density	Min	2.7	gr/cm ³
--------------	-----	-----	--------------------

Cold crushing strength)

after 5 hr drying at 110 Ć	Min	500	Kg/cm ²
after 5 hr firing at 1200 Ć	Min	380	Kg/cm ²