



# PALAR-SANAT-CO

## TECHNICAL DATA

### PULC-60

PRODUCT TYPE	Dense Refractory Castable Ultra Low cement castable :
Main component	fireclay & andalusite
Type of bond	hydraulic
Maximum service temperature	1600 C°
Installation method	casting - Vibrating
Storage	3 month
Packing	25 Kg sacks
grain size	0 - 6 mm
Water required for mixing on site	5.5 - 6.5 litres per 100 Kg of dry material

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

### CHEMICAL ANALYSIS ( Calcined basis)

	Min	Max	Units
Al <sub>2</sub> O <sub>3</sub>	60		%
SiO <sub>2</sub>	29		%
Fe <sub>2</sub> O <sub>3</sub>	1.5		%
CaO	1.2		%

### PHYSICAL PROPERTIES

Bulk density	Min	2.5	gr/cm <sup>3</sup>
--------------	-----	-----	--------------------

### Cold crushing strength (c.c.s)

after 5 hr drying at 110 C°	Min	350	Kg/cm <sup>2</sup>
after 5 hr firing at 1200 C°	Min	700	Kg/cm <sup>2</sup>