



TECHNICAL DATA

PLC-97

PRODUCT TYPE	Dense Refractory Castable Low cement castable :
Main component	Tabular Alumina
Type of bond	hydraulic
Maximum service temperature	1800 C°
Installation method	casting - Vibrating
Storage	3 month
Packing	25 Kg sacks
grain size	0 - 6 mm
Water required for mixing on site	6 - 7 litres per 100 Kg of dry material

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

CHEMICAL ANALYSIS (Calcined basis)

	Min	Max	Units
Al ₂ O ₃	97		%
SiO ₂	0.1		%
Fe ₂ O ₃	0.1		%
CaO	2.1		%

PHYSICAL PROPERTIES

Bulk density	Min	Max	Units
	3		gr/cm ³

Cold crushing strength (c.c.s)

	Min	Max	Units
after 5 hr drying at 110 C°	800		Kg/cm ²
after 5 hr firing at 1200 C°	650		Kg/cm ²