



# PALAR-SANAT-CO

## TECHNICAL DATA

### PAL MAG-94

PRODUCT TYPE	TapHold Mixes(Lodka)
Maximum service temperature	1700 C
Main component	Magnesit
Type of bond	chemical - ceramic
Packing	25 Kg sacks
Storage	6 month
Installation method	Ramming & Casting
grain size	0-3 mm
Water required for mixing on site	10-20 litres/100Kg

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

### CHEMICAL ANALYSIS

MgO	Min	93	%
Fe <sub>2</sub> O <sub>3</sub>	Max	1.5	%
SiO <sub>2</sub>	Max	2	%

### PHYSICAL PROPERTIES

Bulk density	*****	gr/cm <sup>3</sup>
Apparent Porosity	*****	Vol -%

### Cold crushing strength ccs

after 5 hr drying at 110 C	.....	Kg/cm <sup>2</sup>
after 5 hr firing at 1200 C	.....	Kg/cm <sup>2</sup>