



PALAR-SANAT-CO

TECHNICAL DATA

PLC-93sp

PRODUCT TYPE	High alumina dense refractory castable Low cement castable :
Main component	Tabular Alumina & Spinel
Type of bond	hydraulic
Maximum service temperature	1850 C°
Installation method	casting - vibration
Storage	3 month
Packing	25 Kg sacks
grain size	0 - 6 mm
Water required for mixing on site	5.5 - 6.5 litres per 100 Kg of dry material

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

CHEMICAL ANALYSIS (Calcined basis)

Al ₂ O ₃	Min	93	%
SiO ₂	Max	0.2	%
Fe ₂ O ₃	Max	0.1	%
CaO	Max	1.8	%
MGO	Min	5	

PHYSICAL PROPERTIES

Bulk density	Max	2.95	gr/cm ³
--------------	-----	------	--------------------

Cold crushing strength (c.c.s)

after 5 hr drying at 110 C°	Min	800	Kg/cm ²
after 5 hr firing at 1200 C°	Min	1100	Kg/cm ²