



# PALAR-SANAT-CO

## TECHNICAL DATA

### PLC-94cr

PRODUCT TYPE	High alumina dense refractory castable Low cement castable :
Main component	alumina - chrom
Type of bond	hydraulic
Maximum service temperature	1820 C°
Installation method	casting - vibration
Storage	3 month
Packing	25 Kg sacks
grain size	0 - 6 mm
Water required for mixing on site	4.8 - 5.5 litres per 100 Kg of dry material

PRODUCT PROPERTIES	VALUES	UNITS
--------------------	--------	-------

### CHEMICAL ANALYSIS ( Calcined basis)

Al <sub>2</sub> O <sub>3</sub>	Min	94	%
SiO <sub>2</sub>	Max	0.5	%
Fe <sub>2</sub> O <sub>3</sub>	Max	0.1	%
CaO	Max	1.6	%
Cr <sub>2</sub> O <sub>3</sub>	Min	3.5	

### PHYSICAL PROPERTIES

Bulk density	Max	3	gr/cm <sup>3</sup>
--------------	-----	---	--------------------

### Cold crushing strength (c.c.s)

after 5 hr drying at 110 C°	Min	800	Kg/cm <sup>2</sup>
after 5 hr firing at 1200 C°	Min	1100	Kg/cm <sup>2</sup>